



PBFDA

6	8		
	-	2	
)

Article description:	PBFDA (Universal ePTFE sealings, premium)
Article forms:	Universal-F premium: especially for the food and pharmaceutical industry
Preparations:	Without any additionally preparation
Materials:	100% pure, monodirectional expanded PTFE (self-adhesive)

Mechanical properties:

- Best adaptation to all surfaces
- Perfect compensation of unevenness and sealing surface
- UV resistant, no aging
- Suitable for food contact
- Pressure resistance Vacuum up to 200 bar, but always dependent on the installation situation*

Thermal properties:

- From -268 °C to 270 °C
- Short-term 315 °C possible

Recommended application range:

- Temperatures from -160 °C to 150 °C

Chemical properties:

- pH 0 to 14
- Resistant to all media
- Not resistant to dissolved and molten alkali metals as well as elemental fluorine at high temperatures and pressures

* Note: The indicated temperatures and pressures are standard values and can not necessarily occur simultaneously.

Physiological safety

- Physiologically harmless, within the recommended field of application
- Non-toxic, biologically inert

Examinations and approvals:

- BAM tested for use with oxygen
- TÜV product monitored and certified
- TA-Luft tested and blow-out-proof according to VDI 2200
- DVGW tested
- FDA 21 CR 177.1550 compliant
- EC1935/2004 tested for food contact

Page 1 of 2

Gaskets PTFE sealings PBFDA Rev. 02 (13.05.2019)






Applications:

Pipeline flanges, container sealing, heat exchangers, apparatus engineering, flue gas pipelines, email coated plants, reactors, machine casings, pumps, pharmaceutical and food processing plants.

Dimensions:	Universal-F premium:	Band width 3 - 40 mm
		Thickness: 1.5 - 8 mm



Application limits:

Area 2: Max. Application limits, after prior technical verification

The above information is based on the current state of our knowledge of the product and is made to the best of our knowledge and belief. A warranty claim cannot be derived from this information. Information and values always need to be checked by the customer.

All previous issues hereby lose their validity.

Gaskets PTFE sealings PBFDA Rev. 02 (13.05.2019)